



DIVERSIFIED

TESTING LABORATORIES, INC.

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

February 17, 2011

Mr. Gerry Hogan
NORTHEAST TEXTILES, INC.
1750 Hwy. 321 N
Clover, SC 29710

Reference: Laboratory Test Report
Lab Identification No. 6936
Invoice No. 28414 (Attached)

Dear Mr. Hogan:

One (1) fabric sample, identified as **STYLE: MADISON AVENUE**, was received and tested in accordance with the National Fire Prevention Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2010 Edition, (Test 1, Small Scale)". The results are as follows:

<u>Specimen Number</u>	<u>Residual Flame</u> (seconds)	<u>Weight Loss</u> (percent)
1	0.0	13.92
2	0.0	13.56
3	0.0	18.51
4	0.0	17.24
5	0.0	19.40
6	0.0	23.65
7	0.0	21.72
8	0.0	22.16
9	0.0	18.62
10	0.0	19.77
AVG.	0.0	18.86

The fabric sample submitted meets the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Karon S. Matkins

KSM/mr
Attachment