

DIVERSIFIED

TESTING LABORATORIES, INC.

"We Test Per Your Request" →

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

September 20, 2004

Tested For: Charles Cox
Northeast Textiles, Inc.
759 E Lincoln Avenue
Rahway, NJ 07065

Reference: Laboratory Test Report
Lab Identification No. 1979
Invoice No. 4912 (Attached)

SATIN STRIPE M92000


One (1) fabric sample, identified as STYLE: 051/8360; COLOR: 60489 DYE LOT: 83769, was received and tested in accordance with the National Fire Prevention Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 1999 Edition, (Test 1, Small Scale)". The results are as follows:

<u>Specimen Number</u>	<u>Residual Flame (seconds)</u>	<u>Weight Loss (percent)</u>
1	0.0	20.50
2	0.0	15.22
3	0.0	21.56
4	0.0	22.77
5	0.0	24.76
6	0.0	21.03
7	0.0	22.25
8	0.0	19.92
9	0.0	25.73
10	0.0	21.84
AVG.	0.0	21.58

The fabric sample submitted meets the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,


Bobby E. Puett

BEP/ml
Attachment

OUR LETTERS AND REPORTS ARE FOR THE EXCLUSIVE USE OF THE CLIENT TO WHOM THEY ARE ADDRESSED. ANY COMMUNICATION TO OTHERS OR THE USE OF OUR COMPANY NAME MUST RECEIVE PRIOR APPROVAL. OUR TEST RESULTS APPLY ONLY TO THE SAMPLE TESTED AND ARE NOT NECESSARILY INDICATIVE OF THE QUALITIES OF APPARENTLY IDENTICAL OR SIMILAR PRODUCTS. SAMPLES NOT DESTROYED IN TESTING ARE RETAINED A MAXIMUM OF THIRTY DAYS. THE LETTERS, REPORTS OR NAME OF DIVERSIFIED TESTING LABORATORIES, INC. MAY NOT BE USED IN ADVERTISING TO THE GENERAL PUBLIC.