



The

Govmark

Organization, Inc.

96D Allen Blvd.,
 Farmingdale NY 11735
 TEL: (631) 293-8944
 FAX: (631) 293-8956

Page 1

Received: 03/03/2004 | Completed: 03/12/2004 | Letter: M1 | rb | P.O.#: | Test Report #: 2-49820-1-RP

Client's Identification | Pattern: 3/4" Voile Box

Tested For: **Charles Cox** | Key Test: NFPA 701-99 TM#1 5L
 Northeast Textiles, Inc. | Tel: 1-(800)-214-9932 | Ext:
 759 E Lincoln Avenue | Fax: 1-(732)-815-1918
 Rahway, NJ 07065

PC: 0.5H

TEST PERFORMED: NFPA 701 - Standard Methods of Fire Tests for Flame Propagation of Textiles and Films (Not Exceeding 700 g/m²) - 1999 Edition - Test Method #1 (see Note on page 3)

PRODUCT CONFIGURATION: Single Layer; Multi Layer

RESULTS REPORTED: Initially; After 3 dry cleanings; After 5 launderings @ 160°F

RESULTS:

Specimen #	Afterflame* (seconds)	Flaming Drip (seconds)	Weight Loss (percent)	Flame Projects Above Top Of Specimen (yes/no)
1	0.0	0	28.1	No
2	0.0	0	37.5	No
3	0.0	0	29.0	No
4	0.0	0	31.3	No
5	0.0	0	29.0	No
6	0.0	0	30.3	No
7	0.0	0	32.4	No
8	0.0	0	30.3	No
9	0.0	0	33.3	No
10	0.0	0	33.3	No
		Mean: 0	Mean: 31.5	

STATISTICAL VALUES: SD = 2.8 3 SD = 8.4 Mean + 3 SD = 39.8

ABBREVIATIONS USED: SD = Standard deviation.

APPROXIMATE WEIGHT OF MATERIAL (as measured by Govmark): 52 g/m²

PRECONDITIONING: 0.5 hr @ 220°F (Standard)
 24 hrs @ 68±9°F (Alternate: Material shrinks/distorts @ 220°F)

CONVERSION FACTOR: g/m² × 28.35 × .835 = oz/yd²

NOTE:

- All specimens prepared in the length direction.
- See addendum for individual specimen weights.

REMARKS: None.



96D Allen Blvd.,
 Farmingdale NY 11735
 TEL: (631) 293-8944
 FAX: (631) 293-8956

Received: 03/03/2004 | Completed: 03/12/2004 | Letter: M1 | rb | P.O.#: | Test Report #: 2-49820-1-RP

Client's Identification | Pattern: 3/4" Voile BOX

Tested For: **Charles Cox** | Key Test: NFFA 701-99 TM#1 5L
 Northeast Textiles, Inc.
 759 E Lincoln Avenue | Tel: 1-(800)-214-9932 | Ext:
 Rahway, NJ 07065 | Fax: 1-(732)-815-1918

FAILURE CRITERIA: As cited by NFFA 701 - 1999 Edition Test Method #1 (see Comments on page 3)

Afterflame	Flaming Drip Mean	Weight Loss (percent)	
		Mean	Individual Specimen
*	Exceeds 2 seconds	Exceeds 40%	Exceeds Mean + 3 SD

CONCLUSION: Based on the Results on page 1 and the above Failure Criteria cited by NFFA 701 - 1999 Edition Test Method #1, the item tested:

Passes; [] Fails; [] Requires testing of 10 additional specimens
 i.e. only one individual specimen failure was noted

REVISED FAILURE CRITERIA (see Comments on page 3):


Afterflame	Flaming Drip Mean	Weight Loss		Flame Height (Individual Specimen)
		Mean	Ind. Spec.	
*	Exceeds 2 seconds	Exceeds 40%	Exceeds 50%	Projects above top of specimen

CONCLUSION: Based on the Results on page 1 and the above Revised Failure Criteria, the item tested:

Passes; [] Fails; [] Requires testing of 10 additional specimens
 i.e. only one individual specimen failure was noted

* Afterflame is required to be recorded; however, the NFFA document does not factor it into the Failure Criteria reporting requirements. It should be noted that excessive afterflames (15 seconds or more) could be cause for rejection by local fire authorities performing "match" field tests.

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by NFFA 701 - 1999 Edition Test Method #1 with additional recording of flame height.



 AUTHORIZED SIGNATURE
 THE GOVMARK ORGANIZATION, INC. /jd



Received: 03/03/2004	Completed: 03/12/2004	Letter: MI	rb	P.O.#:	Test Report #:	2-49820-1-RP
Client's Identification	Pattern: 3/4" Voile Box					
Tested For: Charles Cox Northeast Textiles, Inc. 759 E Lincoln Avenue Rahway, NJ 07065			Key Test: NFPA 701-99 TM#1 SL Tel: 1-(800)-214-9932 Ext: Fax: 1-(732)-815-1918			

COMMENTS:

The Govmark Org., Inc. has determined to establish failure criteria over and above the criteria spelled out in the NFPA document. The rationale for the "revised" criteria is as follows:

Weight Loss - Individual Specimen Failure:

The NFPA 701 document, as written, provides for a statistical calculation which provides for retest and a potential failure if any individual value exceeds the mean by three standard deviations. Govmark is of the opinion that this cannot mathematically occur, i.e. no individual result is mathematically capable of exceeding the mean plus three standard deviations. Therefore, Govmark has established 50% as the absolute number for individual specimen criteria.

Individual Specimen - Flame Projects Above Top of Specimen:

When NFPA introduced the weight loss criteria, this was hailed as a more objective measure of product performance over previous editions, which relied on visual measurements of fire degradation. Unforeseen were those products which are composed of finishes over substantially non burning substrates. Intense flaming of the finishes occurs without substantially reducing the total weight of the specimen that was tested. It is believed that similar behavior of the intensely burning surface finishes on products made from such material could result in the ignition of nearby combustibles.

NOTE (April 2000):

The NFPA 701 - 1999 Edition supersedes the NFPA 701 - 1996 Edition. The step-by-step test implementation and test failure criteria are the same for both the 1996 Edition and the 1999 Edition. Therefore, it is assumed that this 1999 Edition test report will also satisfy any building code which cites the 1996 Edition.