



96-D Allen Boulevard  
 Farmingdale, New York 11735-5626 USA  
 Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956  
 e-mail: info@govmark.com

Received: 01/11/2007 Completed: 01/22/2007 Letter: U1 her P.O.#: Test Report #: 2-65752-1-

Client's Identification: Pattern # 600 Turkish Taffey

Tested For: Charles Cox Key Test: NFPA 701-2004 TM#1 SL 200  
 Northeast Textiles, Inc.  
 759 E Lincoln Avenue Tel: 1-(800)-214-9932 Ext:  
 Rahway, NJ 07065 Fax: 1-(732)-815-1918

PC: 0.5H

TEST PERFORMED: NFPA 701 - Standard Methods of Fire Tests for Flame Propagation of Textiles and Films - 2004 Edition - Test Method #1

PRODUCT CONFIGURATION:  Single Layer;  Multi Layer

RESULTS REPORTED:  Initially;  After 3 dry cleanings;  After 5 launderings @ 120°F

RESULTS:

Specimen #	Afterflame* (seconds)	Flaming Drip (seconds)	Weight Loss (percent)	Flame Projects Above Top Of Specimen (yes/no)
1	0	0	22.7	No
2	0	0	15.9	No
3	0	0	20.9	No
4	0	0	21.4	No
5	0	0	20.0	No
6	0	0	11.9	No
7	0	0	16.3	No
8	0	0	20.9	No
9	0	0	28.9	No
10	0	0	27.3	No
	Mean:	0	Mean: 20.6	

STATISTICAL VALUES: SD = 5.1 3 SD = 15.3 Mean + 3 SD = 36.6

ABBREVIATIONS USED: SD = Standard deviation.

APPROXIMATE WEIGHT OF MATERIAL (as measured by Govmark): 76 g/m<sup>2</sup>

PRECONDITIONING:  0.5 hr @ 220°F (Standard)  
 24 hrs @ 60±9°F (Alternate: Material shrinks/distorts @ 220°F)

CONVERSION FACTOR: g/m<sup>2</sup> + 28.35 x .833 = oz/yd<sup>2</sup>

NOTE:

- All specimens prepared in the length direction.
- See addendum for individual specimen weights.

REMARKS: None.

Received: 01/11/2007	Completed: 01/22/2007	Letter: U1	her	P.O.#:	Test Report #:	2-65752-1-
Client's Identification	Pattern # 600 Turkish Taffey					
Tested For: Charles Cox			Key Test: NFPA 701-2004 TM#1 5L		200	
Northeast Textiles, Inc.			Tel: 1-(800)-214-9932		Ext:	
759 E Lincoln Avenue			Fax: 1-(732)-815-1918			
Rahway, NJ 07065						

FAILURE CRITERIA: AS cited by NFPA 701 - 2004 Edition Test Method #1 (see Comments on page 3)

Afterflame	Flaming Drip (Mean)	Weight Loss (percent)	
		Mean	Individual Specimen
*	Exceeds 2 seconds	Exceeds 40%	Exceeds Mean + 3 SD

CONCLUSION: Based on the Results on page 1 and the above Failure Criteria cited by NFPA 701 - 2004 Edition Test Method #1, the item tested:

Passes;  Fails;  Requires testing of 10 additional specimens  
i.e. only one individual specimen failure was noted

REVISED FAILURE CRITERIA (see Comments on page 3):

Afterflame	Flaming Drip (Mean)	Weight Loss		Flame Height (Individual Specimen)
		Mean	Ind. Spec.	
*	Exceeds 2 seconds	Exceeds 40%	Exceeds 50%	Projects above top of specimen


CONCLUSION: Based on the Results on page 1 and the above Revised Failure Criteria, the item tested:

Passes;  Fails;  Requires testing of 10 additional specimens  
i.e. only one individual specimen failure was noted

~~Attention is required to be recorded; however, the NFPA document does not factor it into the Failure Criteria reporting requirements. It should be noted that excessive afterflames (15 seconds or more) could be cause for rejection by local fire authorities performing "match" field tests.~~

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by NFPA 701 - 2004 Edition Test Method #1 with additional recording of flame height.

  
-----  
AUTHORIZED SIGNATURE  
THE GOVMARK ORGANIZATION, INC. /rb



96-D Allen Boulevard  
Farmingdale, New York 11735-5826 USA  
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8966  
e-mail: info@govmark.com

Received: 01/11/2007	Completed: 01/22/2007	Letter: U1	bcg	P.O.#:	Test Report #:	2-65752-1-
Client's Identification	Partem # 600 Turkish Taffey					
Tested For: Charles Cox Northeast Textiles, Inc. 759 E Lincoln Avenue Rahway, NJ 07065			Key Test: NFPA 701-2004 TM#1 SL			200
			Tel: 1-(800)-214-9932		Ext:	
			Fax: 1-(732)-815-1918			

COMMENTS:

The Govmark Org., Inc. has determined to establish failure criteria over and above the criteria spelled out in the NFPA document. The rationale for the "revised" criteria is as follows:

Weight Loss - Individual Specimen Failure:

The NFPA 701 document, as written, provides for a statistical calculation which provides for retest and a potential failure if any individual value exceeds the mean by three standard deviations. Govmark is of the opinion that this cannot mathematically occur, i.e. no individual result is mathematically capable of exceeding the mean plus three standard deviations. Therefore, Govmark has established 50% as the absolute number for individual specimen criteria.

Individual Specimen - Flame Projects Above Top of Specimen:

When NFPA introduced the weight loss criteria, this was hailed as a more objective measure of product performance over previous editions, which relied on visual measurements of fire degradation. Unforeseen were those products which are composed of finishes over substantially non burning substrates. Intense flaming of the finishes occurs without substantially reducing the total weight of the specimen that was tested. It is believed that similar behavior of the intensely burning surface finishes on products made from such material could result in the ignition of nearby combustibles.

(Page 3 of 3)

The results contained in this report relate only to item(s) tested. The test report shall not be reproduced, except in full, without written approval from The Govmark Organization, Inc.