


Received:08/18/2010	Completed:08/25/2010	Letter: S1	rb	P.O.#:	Test Report #:	2-52542-1-
Client's Identification	Waterfall, 100% polyester inherently FR					
Tested For: Charles Cox Northeast Textiles, Inc. 759 E Lincoln Avenue Rahway, NJ 07065			Key Test: AATCC 135 Dimen Chg/Multi Eval 1&20 Tel: 1-(800)-214-9932 Fax: 1-(732)-815-1918			160 Ext:
PC: 4H						
TEST PERFORMED: AATCC Test Method 135 Dimensional Changes in Automatic Home Laundering of Woven & Knit Fabrics						
NUMBER OF LAUNDERING CYCLES: 1 & 20 WASH LOAD: 4 lbs						
LAUNDERING PROCEDURE: Wash Machine Setting Wash Temperature Tumble Dry ----- Normal/cotton/sturdy 160°F ± 5°F Cotton/sturdy						
RESULTS: (Note: In addition to recording dimensional changes, other properties are physically evaluated as per client's request.)						
Evaluation For:						
	After 1 Cycle		After 20 Cycles			
	-----		-----			
1. Dimensional Stability	(% change)		(% change)			
	-----		-----			
(- indicates shrinkage)	Length	Width	Length	Width		
(+ indicates elongation)	-----	-----	-----	-----		
	0.0	0.0	-0.05	0.0		
	0.0	0.0	-0.05	0.0		
	0.0	0.0	-0.05	0.0		
	-----	-----	-----	-----		
	Av: 0.0	0.0	Av: -0.05	0.0		
2. Pilling:	None		None			
3. Fuzzing:	None		None			
4. Wrinkling:	None		None			
5. Color retention:	No change		No change			
6. Snagging:	None		None			
REMARKS: None.						
CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by AATCC Test Method 135.						
 ----- AUTHORIZED SIGNATURE THE GOVMARK ORGANIZATION, INC. /jd						
						(Page 1 of 2)

Received: 08/18/2010 | Completed: 08/25/2010 | Letter: S | rb | P.O.#: | Test Report #: 2-52542-0-

Client's Identification: Waterfall, 100% polyester inherently FR

Tested For: **Charles Cox** Key Test: ASTM D 3512 190
 Northeast Textiles, Inc.
 759 E Lincoln Avenue Tel: 1-(800)-214-9932 Ext:
 Rahway, NJ 07065 Fax: 1-(732)-815-1918

PC: 4H CODE: 95-190

TEST PERFORMED:

ASTM D 3512 - Standard Test Method for Pilling Resistance and Other Related Surface Changes of Textiles
 Fabrics: Random Tumble Pilling Tester Method

RESULTS:

Specimen #	Rating After 30 Minutes	Rating After 60 Minutes
1	Class 5	Class 5
2	Class 5	Class 5
3	Class 5	Class 5

REMARKS:


None.

RATING SYSTEM:

- Class 5 - No pilling
- Class 4 - Slight pilling
- Class 3 - Moderate pilling
- Class 2 - Severe pilling
- Class 1 - Very severe pilling

CERTIFICATION:

I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by ASTM D 3512.



 AUTHORIZED SIGNATURE
 THE GOVMARK ORGANIZATION, INC. /jd