



# DIVERSIFIED

TESTING LABORATORIES, INC.  
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET  
P.O. BOX 4004  
BURLINGTON, NORTH CAROLINA 27215  
PHONE (336) 227-7710 • FAX (336) 227-1175  
www.diversifiedtestinglabs.com

November 1, 2013

Mr. Ken Dollar  
NORTHEAST TEXTILES, INC.  
P.O. Box 2147  
Gaffney, SC 29342

Reference: Laboratory Test Report  
Lab Identification No. 8099  
Invoice No. 38831 (Attached)

Dear Mr. Dollar:

One (1) fabric sample, identified as **ECLIPSE**, was received and tested in accordance with the National Fire Prevention Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2010 Edition, (Test 1, Small Scale)". The results are as follows:

<u>Specimen Number</u>	<u>Residual Flame</u> (seconds)	<u>Weight Loss</u> (percent)
1	0.0	10.26
2	0.0	7.25
3	0.0	16.37
4	0.0	16.47
5	0.0	10.61
6	0.0	15.37
7	0.0	15.19
8	0.0	13.72
9	0.0	17.60
10	<u>0.0</u>	<u>15.05</u>
AVG.	0.0	<u>13.79</u>

The fabric sample submitted **meets** the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Bobby E. Puett

BEP/mr  
Attachment